

# 60D

# CONCRETE



## DESCRIPTION

The 60D Concrete is made of cement, high quality aggregates and last generation additives. These components guarantee a good performance fulfilling the requirements of the client. This type of concrete takes 60 days to reach its compressive strength.

## TECHNICAL SPECIFICATIONS

- Maximum size of the aggregate: 25 mm.
- Nominal maximum size of the aggregate: 19 mm.
- Slump: 150 mm  $\pm$  20 mm.
- Compressive strength: 175 kg/cm<sup>2</sup> - 450 kg/cm<sup>2</sup>.
- Density: 2300 kg/m<sup>3</sup>.
- Temperature: 84° F.
- Volume of air content: 1.5%
- Initial setting time: 4 hours
- Final setting time: 8 hours
- Pozzolana hydraulic cement (MP/A type)

## USES

In general, 60D concrete has been designed to be used in different elements of the construction where it is not required to early reach the strength, so it can be reached in a period of 60 days. For example: slabs, walls, sidewalks, stormwater outfall, concrete curbs, among others.

## ADVANTAGES

- Eco-friendly concrete.
- Specialized advising in the concrete technology.
- Strict quality control.
- High quality materials.
- Automatic dosing system.
- Economic benefit.

## PROPERTIES

Mix concrete component materials comply with all the corresponding regulations.

- MP/A cement complies with the 479:2015 Technical Regulations of Hydraulic Cement (RTCR, acronym in Spanish).
- River aggregates comply with the ASTM C33 International Regulation.
- Plasticizers and retarding admixtures satisfy the ASTM C94 International Regulations.
- Clean water complies with the requirements of the ASTM C94 International

## QUALITY CONTROL

The development and research laboratory of AMCO has technicians certified by the ACI (American Concrete Institute). Therefore, different tests are executed correctly guaranteeing reliable results.

Daily, random samples are taken from the different types of concrete and cylindrical compression and beam flexural tests are conducted for internal control. Monitoring and quality control of the concrete is maintained to provide the customer with the desired product.

## PLACEMENT

- Direct discharge
- Pumping discharge

## SUGGESTIONS

AMCO guarantees the delivery of 60D Concrete in ideal conditions. It reaches compressive strength at 60 days old. Do not alter the product with water or any other substance.

The maximum concrete unloading time is one hour since it arrives at the place. For this reason, the client should plan the correct logistic to meet this requirement.



Awarded by the Bandera Azul Ecológica program for our efforts in environmental impact reduction.

 **2509-9800**



E-mail: [ventas@amco.co.cr](mailto:ventas@amco.co.cr) / [www.amcocr.com](http://www.amcocr.com)